

Test report no.: BEA 2015149

Date: 30.9.2015

Client: Biotel d.o.o.
Attn.: Mrs. Tamara Haiden
Slatina 1bb
84320 Andrijevica
Montenegro

Order: from 18.09.2015

Subject: 1 sample wood pellets, approx. 5 kg

Receipt of samples: 24.09.2015, the sample was delivered by courier service.


Content: The tests were carried out according to ISO 17225-2.

Analysis period: 28.-30.09.2015

Results:

Sample 2015149	Standard	unit	Pellets	Limit values according ENplus	
				Class A1	Class A2
mechanical durability	EN15210-1	[%]	98,8	≥ 98,0	≥ 97,5
bulk density	EN 15103	[kg/m ³]	628	≥ 600	≥ 600
moisture content	EN 14774-2	[%]	7,3	≤ 10	≤ 10
ash content 550°C (db)	EN 14775	[%]	1,1	≤ 0,7	≤ 1,2

Director in charge



Dr. Martin Englisch



The test results apply only to the samples investigated. The correctness of the sampling can only be guaranteed, if this was done by BEA staff according to the order. Test Reports and expert opinions may only be made available to third parties, either free of charge or against payment, if the full wording is given and if the author is expressly named. The General Terms and Conditions of BEA Institut für Bioenergie GmbH shall apply as amended.